

POLAPLAST P25

Two-component coat material for Equestrian rubber flooring system.

GENERAL CHARACTERISTICS

POLAPLAST P25 is a pigmented and solvent-free, thixotropic, two-component, polyurethane, semi-elastic material with high tensile strength properties, environment friendly, colorful and easy-to-apply, safe to construction.

POLAPLAST P25 shows excellent resistance to moisture during the curing phase and a good curing behavior even at low temperature.

TECHNICAL DATA

Mixing Ratio	88,63 : 11,37 (By weight)
Density of mixture (25°C)	1,48-1,58 Kg/L
Viscosity (25°C)	50000-85000 mPa.s
Pot-life (23°C)	30-75 min.
Application temperature	Min 10°C
Curing (20°C and %60 relative humidity)	After 24 hours it cures.
Color	KDF colorchart

PREPARATION- APPLICATION

Applied on dry surfaces, free of materials that might prevent bonding e.g. dust, loose particles, grease etc (in case of asphalt or concrete). The success in the application depends on the right preparation of the underlay and use of the material.

POLAPLAST P25 is used in **POLTRACK EQUINE SYSTEM**, a synthetic, seamless flooring for horse stalls, barns, paddocks etc.

POLAPLAST P25 is applied on top of the sealing layer **POLAPLAST P24** which seals the top of prefabricated cushion or in situ installed rubber granule subfloors. The subfloor has to be dry, load bearing, clean and free of loose and brittle particles and substances which impair adhesion such as oil, grease, paint or other contaminants.

- Processing temperature of both components should be between 10-40°C.
- The resin component should be thoroughly stirred to incorporate any slight separation, whilst continuing stirring the contents of the hardener container should be added. Continue stirring until a homogeneous mix is obtained. The mixed material must be used within 30-75 minutes of mixing at 20°C.

- The well mixed material is applied with a notched trowel 5,5 mm.
- Substrate temperatures must not exceed 50°C as this would liquefy the material and increase the coverage.
- At low temperature and humidity, the speed of reaction is reduced resulting in a longer pot life, re-coating interval and open time. The speed of reaction is accelerated at high temperatures and humidity and the converse is true. Direct sunshine shortens the time frames considerably.
- During the first hours after application, the coating had to be protected from direct contact with water as this could cause foaming of the material. In case of (expected) rain, **POLAPLAST P25** should not be applied.
- Sealed surface with **POLAPLAST P25** can be recoated during the first 48 hours after application without the use of primer if the surface is dry and clean.

CONSUMPTION

2.3kg/m²

APPLICATION TOOLS

Notched trowel. Tools should be cleaned with **PU SOLVENT** immediately after use.



PACKAGING

Set of 250kg (barrels), set of 34kg(drums)



STORAGE

12 months in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30°C (avoid sunlight).

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the material safety data sheet.



Sports Flooring Systems & Building Materials
50 YEARS OF EXPERIENCE

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

KDF - Kataskeves Dapedon LTD
e : exports@kdf.gr w : www.kdf.gr

Headquarters/Showroom Office
19th km National Road Thessaloniki-Moudania
57001, Neo Rysio, Thessaloniki, Greece
t / f : +30 2310 829598

