

## POLYSPORT 952-GLOSSY

POLYURETHANE-BASED, TWO-COMPONENT, GLOSSY FINISH ALIPHATIC COATING

### GENERAL CHARACTERISTICS

**POLYSPORT 952-GLOSSY** is a polyurethane, two-component, solvent-based, with glossy finish aliphatic coating for indoor sports surfaces.

- It is applied on polyurethane, self-leveling coating **POLYSPORT PU 951** as a final, sealing layer of a multilayer polyurethane floor especially designed for sport halls such as tennis, basketball, handball, volleyball and multipurpose halls.
- It is applied easily with short-haired mohair roller and airless sprayer.
- Provides a surface with anti-slip properties.

### TECHNICAL DATA

|                                                             |                                  |
|-------------------------------------------------------------|----------------------------------|
| Basis:                                                      | two-component polyurethane paint |
| Appearance:                                                 | liquid                           |
| Colors:                                                     | KDF colorchart                   |
| Viscosity(25°C):                                            | 200 - 600 mPas                   |
| Density(25°C):                                              | 1.08 - 1.18 kg/l                 |
| Mixing proportion (A:B):                                    | 78 : 22 by weight                |
| Temperature for the application and drying of the material: | 15 – 40°C                        |

### PREPARATION-APPLICATION

Applied on dry surfaces without rising humidity issues, free of materials that might prevent bonding e.g. dust, loose particles, grease etc (in case of asphalt or concrete). The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry** cleaning of the surface from dust and residues using vacuum cleaner and squeegee.
- Caution must be taken so that temperature of the support surface as well as ambient air remains above 15°C during application and curing of the materials while relative humidity does not exceed 75%.
- Application of prefabricated sub-floor **ISOPOL 854** using **PU FLEX 140** or wet-pour rubber cushion mixture of SBR rubber and **PU BINDER 1118**.
- Sealing of surface porosity of **ISOPOL 854** or wet-pour rubber cushion mix of SBR rubber and **PU BINDER 1118** using elastic pore sealer **POLYSPORT STUCCO 950** and application of self-leveling coating **POLYSPORT PU 951**.

KDF - Kataskeves Dapedon LTD  
e : exports@kdf.gr w : www.kdf.gr

Headquarters/Showroom Office  
19<sup>th</sup> km National Road Thessaloniki-Moudania  
57001, Neo Rysio, Thessaloniki, Greece  
t / f : +30 2310 829598



- The next day, depending on the ambient temperature follows the application of **POLYSPORT 952-GLOSSY** in two crossed layers. The second layer is applied after the first layer has dried (within 24h). Components A & B (hardener) packed into separate containers in fixed weight proportions are mixed together using a low revolution mixer (300-600 rpm) for 1-2 min. Stirring of the mixture should be performed thoroughly near the sides and bottom of the container in order to achieve uniform dispersion of the hardener.
- The application is done by airless sprayer or short-haired mohair roller in 2 crossing layers.

## CONSUMPTION

App.200-250 gr/m<sup>2</sup>, for two layers.

## APPLICATION TOOLS

Short-haired mohair roller or airless sprayer. Tools should be cleaned with **PU SOLVENT** immediately after use.



## PACKAGING

Set of 20 Kg (drums).



## STORAGE

12 months in unopened containers in dry places with minimum temperature 5°C and maximum temperature 30°C (avoid sunlight).

## REMARKS

- Working time of **POLYSPORT 952-GLOSSY** decreases when ambient temperature rises.
- Prolonged storage of partially used containers containing **POLYSPORT 952-GLOSSY** must be avoided as contact with atmospheric moisture will result in skinning and clouding of the product.
- All surfaces should be thoroughly cleaned from dust and residues prior each application.
- After hardening **POLYSPORT 952-GLOSSY** is completely safe for health.

## CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

**For more information consult the safety data sheet.**

---

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of KDF LTD.

**KDF - Kataskeves Dapedon LTD**  
e : [exports@kdf.gr](mailto:exports@kdf.gr) w : [www.kdf.gr](http://www.kdf.gr)

**Headquarters/Showroom Office**  
19<sup>th</sup> km National Road Thessaloniki-Moudania  
57001, Neo Rysio, Thessaloniki, Greece  
t / f : +30 2310 829598

